



TEST REPORT

Number : SHAT04358592

Applicant : BETA TEXTILES CO., LTD.
SUITE 618, HUAFANG INTERNATIONAL PLAZA,
NO.178, CHENGBEI ROAD, ZHANGJIAGANG,
JIANGSU
Attn : VERONICA HUANG

Date : Apr 23, 2016

Sample Description As Declared :

No. Of Sample : One
Fibre Content : 50% Polyester 45% Kwikwarm 5% Spandex
Material : Jersey Knitted Fabric
Finishing : -
End Uses : Garment
Colour : Claret Stripe
Style No. : HY162888
Order No./PO No. : -
Buyer's Name : -
Manufacturer's Name : -
Ref. : -

Applicant's Provided Care Instruction/Label: -

Date Received/Date Test Started : Apr 21, 2016

Prepared And Checked By:
For Intertek Testing Services Ltd., Shanghai

Jennifer Ren
Assistant General Manager of Textile Division

TEST REPORT

Number : SHAT04358592

Tests Conducted (As Requested By The Applicant)

- 1 Fabric Moisture Management Properties As Received (AATCC 195-2012, Moisture Management Tester):
Testing Parameter : - Pump On Time 20 seconds.
- Measure Time 120 seconds.

<u>Liquid Moisture Management Indices</u>		<u>Average</u>	<u>Standard Deviation</u>	<u>Grade</u>
- Wetting Time (Second)	- Top Surface	3.4632	0.2198	4.5
	- Bottom Surface	3.5006	0.5021	4.0
- Absorption Rate (%/Second)	- Top Surface	74.1399	2.5134	4.0
	- Bottom Surface	31.8559	9.7637	2.5
- Maximum Wetted Radius (mm)	- Top Surface	22.0	2.7386	4.0
	- Bottom Surface	24.0	2.2361	5.0
- Spreading Speed (mm/Second)	- Top Surface	3.7589	0.1227	4.5
	- Bottom Surface	3.6846	0.1177	4.0
- One-way Transport Index		612.3895	57.573	5.0
- Overall Moisture Management Capability (OMMC)		0.7844	0.0281	4.5

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.